

MACMAT-R

Rev: 08, July 07

PVC GALFAN GALVANISED 6 / 2.2

SPECIFICATIONS		
PROPERTIES		
Туре	Double twist hexagonal woven steel wire mesh onto which a 3D geomat matrix is extruded	
Mesh Type	6 x 8	D
Mesh Wire	2.2mm diameter (BS EN 10218-2 & BS EN 10223-3)	
Selvedge Wire	2.7mm diameter (BS EN 10218-2 & BS EN 10223-3)	D = 60mm (Nominal)
Corrosion Protection	Galfan galvanised (95% Zinc + 5% Aluminium Alloy + Mischmetals) coated to BS EN 10244-2 Class A (230 g/m²) with an extruded grey PVC coating of mean wall thickness of 0.5mm	
Geomat Type	A three dimensional geomat of entangled polypropylene monofilaments, heat bonded at contact points, 10mm thick with a void space of 90%.	
Roll Size / Weight	2m x 25m (Roll Weight = 90 kg (Nominal))	
Jointing	All joints and connections shall be formed with continuous 2.2mm PVC Galfan coated lacing wire and/ or high tensile 3mm diameter Stainless Steel 'C' rings.	
BBA Approval	Maccaferri hexagonal wire mesh is BBA certified for up to 120 years design life. Agrément Certificate No. 95/3141	





Maccaferri reserves the right to alter specifications of its products without notice. Please contact us for the most up to date specifications.

Maccaferri NZ Ltd

14 Goodman Place P.O. BOX 12536, Penrose, Auckland, New Zealand Tel. (+64) 9 6346495 - Fax (+64) 9 6346492, FREEPHONE 0800 60 60 20 E-mail: sales@maccaferri.com - Web site: www.maccaferri.co.nz Quality System AS/NZS ISO 9001:2000

The information presented herein is, to the best of our knowledge and belief, correct and is subject to periodic review and revision. The validity of the information relative to the subsoil, hydraulic and other engineering conditions must be ascertained by a suitably qualified person. No warranty is either expressed or implied. Unauthorised reproduction or distribution is prohibited. Copyright is vested in Maccaferri or Maccaferris' Principal where applicable.